

Araldite[®] 2021-1 Structural Adhesive

Product Description

Araldite[®] 2021-1 structural adhesive is a two components, room temperature curing methacrylate based general purpose adhesive for rapid assembly operations with a wide variety of substrates.

Features

- Working time: 4-5 minutes
- One to one volume mix ratio
- High peel strength
- Multi-purpose
- Excellent bond to a wide range of plastics, composites and metals
- Suitable for service at temperatures up to 212°F (100°C)

Typical Properties*

Property	Araldite [®] 2021-1 A	Araldite [®] 2021-1 B	Mixed System
Appearance	Off white	Beige / yellow	Pale yellow
Density, g/cm ³	1.00	0.95	~1
Viscosity at 25°C (Brookfield, spindle # 7 and at 10 rpm), cPs	287,600	63,200	--
Working time at 25°C, 10 g, min	--	--	4.00-5.00
Flash point (°F)	10	10	--

*Properties are based on Huntsman test methods. Copies are available upon request

Processing

Mix Ratio

Product	Parts by weight	Parts by volume
Araldite [®] 2021-1 A	100	100
Araldite [®] 2021-1 B	95	100

Pretreatment

The strength and durability of a bonded joint are dependent on proper treatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as acetone, iso-propanol (for plastics) or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low-grade alcohol, gasoline, or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching (“pickling”) the degreased surfaces. Abrading should be followed by a second degreasing treatment.

Araldite® 2021-1 structural adhesive is available in cartridges designed for use with disposable 18-21 elements mixing nozzles and can be applied as a ready to use adhesive.

Application of adhesive

The resin/hardener mix may be applied manually or with an automated dispensing equipment to the pretreated and dry joint surfaces. A 0.002 to 0.004 in (0.05 to 0.10 mm) thick adhesive layer will normally impart the greatest lap shear strength to the joint. A proper adhesive joint design is also critical for a durable bond. The joint components should be assembled and maintained in a secure position as soon as the adhesive has been applied. For more detailed explanations regarding surface preparation and pretreatment, adhesive joint design, and the dual syringe dispensing system, visit www.araldite2000plus.com.

Equipment Maintenance

All tools should be cleaned with hot soapy water before the adhesives residues have had time to cure. The removal of cured residues is a difficult and time-consuming operation. If solvents such as acetone are used for cleaning, operators should take the appropriate precautions to avoid skin and eye contact.

Cure times to reach minimum shear strength

Tested at 23°C (73°F) and 55% R. H.	
Cure time to reach lap shear strength > 145 psi (1 MPa), minutes	7
Cure time to reach lap shear strength > 1450 psi (10 MPa), minutes	13

Typical Physical Properties

Unless otherwise stated, the data were determined with typical production batches using standard test methods. They are typical values only, and do not constitute a product specification.

The figures below were all determined by testing standard specimens made by lap-jointing 4.5 x 1.0 x 0.063 in (114 x 25 x 1.6 mm) strips. The bond area was 0.5 x 1.0 in (12.5 x 25 mm) in each case.

Average of 3 test specimens lap shear strength, metal-metal joints. Substrates were degreased with IPA.

Substrate	Substrates were cured at 25°C (77°F) for 24 hours and tested at 23°C (73°F), psi	Substrates were cured at 40°C (104°F) for 16 hours and tested at 23°C (73°F), psi	Test Method
Primed aluminum, 2024T3 Clad	4,140	3,220	ASTM D1002
Treated steel, RC #14	2,860	4,130	ASTM D1002
Stainless steel, V4A	2,930	2,680	ASTM D1002

Average of 3 test specimens lap shear strength, plastic-plastic joints. Substrates were lightly abraded and degreased with IPA.

Substrate	Substrates were cured at 25°C (77°F) for 24 hours and tested at 23°C (73°F), psi	Substrates were cured at 40°C (104°F) for 16 hours and tested at 23°C (73°F), psi	Test Method
ABS	470 (substrate failure)	510 (substrate failure)	ASTM D1002
PVC	830 (substrate failure)	810 (substrate failure)	ASTM D1002
PC	640 (substrate failure)	970 (substrate failure)	ASTM D1002
PMMA	560 (substrate failure)	510 (substrate failure)	ASTM D1002

Average of 3 test specimens lap shear strength on primed aluminum substrates. Substrates were degreased with IPA, cured at 40°C for 16 hours and tested at 23°C, after immersion in 23°C media.

Media	Initial, psi	30 days, psi	60 days, psi	90 days, psi	Test Method
Gasoline	3,220	2,530	2,700	2,670	ASTM D1002
10% Acetic acid	3,220	2,920	3,200	2,680	ASTM D1002
Xylene	3,200	2,980	3,280	3,470	ASTM D1002
Water	3,200	2,810	3,070	3,030	ASTM D1002

Average of 3 test specimens lap shear strength on primed aluminum substrate versus tropical weathering, 92% RH at 40°C. Substrates were degreased with IPA, cured at 40°C for 16 hours and tested at 23°C.

Initial, psi	30 days, psi	60 days, psi	90 days, psi	Test Method
3,220	3,400	3,870	4,240	ASTM D1002

Average of 3 test specimens lap shear strength on primed aluminum substrate versus temperature. Substrates were degreased with IPA and cured at 40°C for 16 hours and tested at different temperature.

-40°C (40°F)	23°C (73°F)	100°C (212°F)	Test Method
2,220 psi	3,220 psi	730 psi	ASTM D1002

Additional properties.

Property	Value	Test Method
T-peel test on primed aluminum substrate, cured at 40°C for 16 hours and tested at 23°C,	7 pli	ASTM D1876 Rev A
Shore D hardness, sample cured at 40°C for 16 hours and tested at 23°C	82	ASTM D2240

Storage

Araldite® 2021-1 may be stored during 18 months at 2°C to 8°C provided the components are stored in the original sealed containers. The expiry date is indicated on the packaging.

The product may be placed at room temperature before use, the total time at room temperature should not exceed 6 months. Long term exposure above 25°C will reduce the shelf life of the product.

Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to SDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Araldite is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all countries.

© 2016 Huntsman Advanced Materials Inc.

Main Offices:

Huntsman Corporation

10003 Woodloch Forest Dr
The Woodlands, TX 77380
888-564-9318

Huntsman Advanced Technology Center

8600 Gosling Rd.
The Woodlands, TX 77381
281-719-7400